



Waterproofing Paving Mat

Specification Sheet – GlasPave25

SPECIFICATIONS FOR USE IN ASPHALT OVERLAYS			
PROPERTY	TEST METHOD	GLASPAVE25	
		METRIC*	IMPERIAL**
TENSILE STRENGTH	ASTM D 5035	1250 N/50mm	140 lb/in.
ELONGATION AT BREAK	ASTM D 5035	≤5%	≤5%
MELTING POINT	ASTM D 276	> 205°C	> 400°F
MASS/UNIT AREA	ASTM D 5261	136 g/m ²	4.0 oz/yd ²
ASPHALT RETENTION	ASTM D 6140	.47 l/m ²	.10 gal/yd ²
STYLE	ASTM D 7239–06	Hybrid Geosynthetic Paving Mat Type 1	Hybrid Geosynthetic Paving Mat Type 1
ROLL LENGTH [†]		228.6 m or 914.4 m	250 yds or 1000 yds
ROLL WIDTH [†]		1.17 m or 2 m	46 in. or 78 in.

[†] Product is sold by the roll. *All metric values are nominal. **All imperial values are approximate.

GlasPave™ is a trademark of Saint-Gobain Technical Fabrics (SGTF).



Tensar International Corporation
 5883 Glenridge Drive, Suite 200
 Atlanta, Georgia 30328
800-TENSAR-1
www.tensar-international.com

GlasPave™ is a trademark of Saint-Gobain Technical Fabrics (SGTF). GlasPave™ is distributed in the United States of America, Canada and certain other countries by Tensar International Corporation (TIC). Inasmuch as SGTF and TIC have no control over installation design, installation workmanship, accessory materials, or conditions of application, SGTF and TIC do no warrant the performance or results of any installation or use of GlasPave™. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose.

©2008, Tensar International Corporation, Limited LLC, Inc.

Exclusive distributor in the Americas for:

