Tensar, a division of CMC

2500 Northwinds Pkwy, Suite 500 Alpharetta, Georgia 30009 Phone: 800-TENSAR-1 www.tensarcorp.com

## **Product Specification - Biaxial Geogrid BXSQ100**

Product Type: Integrally Formed Biaxial Geogrid

Polymer: Polypropylene

## **Product Properties**

Index Properties	Units	MD Values <sup>1</sup>	XMD Values <sup>1</sup>
Aperture Dimensions <sup>2</sup>	mm (in)	38 (1.5)	38 (1.5)
<ul> <li>Rib Thickness<sup>2</sup></li> </ul>	mm (in)	0.7 (0.03)	0.5 (0.02)
<ul> <li>Tensile Strength @ 2% Strain<sup>3</sup></li> </ul>	kN/m (lb/ft)	4.5 (310)	4.5 (310)
<ul> <li>Tensile Strength @ 5% Strain<sup>3</sup></li> </ul>	kN/m (lb/ft)	8.5 (580)	8.5 (580)
<ul> <li>Ultimate Tensile Strength<sup>3</sup></li> </ul>	kN/m (lb/ft)	12.5 (855)	12.5 (855)
Structural Integrity			
■ Junction Efficiency <sup>4</sup>	%	93	
<ul> <li>Overall Flexural Rigidity<sup>5</sup></li> </ul>	mg-cm	160,000	
<ul> <li>Aperture Stability<sup>6</sup></li> </ul>	m-N/deg	0.32	
Durability			
<ul> <li>Resistance to Installation Damage<sup>7</sup></li> </ul>	%SC / %SW / %GP	95 / 93 / 90	
<ul> <li>Resistance to Long Term Degradation<sup>8</sup></li> </ul>	%	100	
<ul> <li>Resistance to UV Degradation<sup>9</sup></li> </ul>	%	100	

## **Dimensions and Delivery**

The biaxial geogrid shall be delivered to the job site in roll form with each roll individually identified and nominally measuring 3.8 meters (12.5 feet) in width and 75.0 meters (246 feet) in length.

## **Notes**

- 1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
- 2. Nominal dimensions.
- 3. Determined in accordance with ASTM D6637-10 Method A.
- 4. Load transfer capability determined in accordance with ASTM D7737-11.
- Resistance to bending force determined in accordance with ASTM D7748/D7748M-14.
- 6. Resistance to in-plane rotational movement measured by applying a 20 kg-cm (2 m-N) moment to the central junction of a 9 inch x 9 inch specimen restrained at its perimeter in accordance with GRI GG9.
- 7. Resistance to loss of load capacity or structural integrity when subjected to mechanical installation stress in clayey sand (SC), well-graded sand (SW), and crushed stone classified as poorly graded gravel (GP). The geogrid shall be sampled in accordance with ASTM D5818 and load capacity shall be determined in accordance with ASTM D6637.
- 8. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
- Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.